

Refractive Indices		BK7
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.48929
$n_{1970.1}$	1970.1	1.49500
$n_{1529.6}$	1529.6	1.50094
$n_{1060.0}$	1060.0	1.50669
$n_t$	1014.0	1.50731
$n_s$	852.1	1.50981
$n_r$	706.5	1.51289
$n_C$	656.3	1.51432
$n_{C'}$	643.8	1.51472
$n_{632.8}$	632.8	1.51509
$n_D$	589.3	1.51673
$n_d$	587.6	1.51680
$n_e$	546.1	1.51872
$n_F$	486.1	1.52238
$n_{F'}$	480.0	1.52283
$n_g$	435.8	1.52669
$n_h$	404.7	1.53024
$n_i$	365.0	1.53626

Constants of Dispersion Formula	
$A_0$	2.2718929
$A_1$	$-1.0108077 \cdot 10^{-2}$
$A_2$	$1.0592509 \cdot 10^{-2}$
$A_3$	$2.0816965 \cdot 10^{-4}$
$A_4$	$-7.6472538 \cdot 10^{-6}$
$A_5$	$4.9240991 \cdot 10^{-7}$