

| Refractive Indices | | SF1 |
|--------------------|----------------|---------|
| | λ [nm] | |
| $n_{2325.4}$ | 2325.4 | 1.67352 |
| $n_{1970.1}$ | 1970.1 | 1.67855 |
| $n_{1529.6}$ | 1529.6 | 1.68450 |
| $n_{1060.0}$ | 1060.0 | 1.69258 |
| n_t | 1014.0 | 1.69372 |
| n_s | 852.1 | 1.69889 |
| n_r | 706.5 | 1.70647 |
| n_C | 656.3 | 1.71032 |
| $n_{C'}$ | 643.8 | 1.71141 |
| $n_{632.8}$ | 632.8 | 1.71245 |
| n_D | 589.3 | 1.71715 |
| n_d | 587.6 | 1.71736 |
| n_e | 546.1 | 1.72311 |
| n_F | 486.1 | 1.73462 |
| $n_{F'}$ | 480.0 | 1.73610 |
| n_g | 435.8 | 1.74916 |
| n_h | 404.7 | 1.76199 |
| n_i | 365.0 | 1.78577 |
| | | |
| | | |
| | | |

| Constants of Dispersion Formula | |
|---------------------------------|----------------------------|
| A_0 | 2.8458754 |
| A_1 | $-9.8260548 \cdot 10^{-3}$ |
| A_2 | $3.2192965 \cdot 10^{-2}$ |
| A_3 | $1.7491597 \cdot 10^{-3}$ |
| A_4 | $-7.8964252 \cdot 10^{-5}$ |
| A_5 | $1.1858651 \cdot 10^{-5}$ |
| | |