

Refractive Indices		SF2
	λ [nm]	
$n_{2325.4}$	2325.4	1.61008
$n_{1970.1}$	1970.1	1.61497
$n_{1529.6}$	1529.6	1.62058
$n_{1060.0}$	1060.0	1.62768
n_t	1014.0	1.62863
n_s	852.1	1.63290
n_r	706.5	1.63902
n_c	656.3	1.64210
$n_{c'}$	643.8	1.64297
$n_{632.8}$	632.8	1.64379
n_D	589.3	1.64752
n_d	587.6	1.64769
n_e	546.1	1.65222
n_F	486.1	1.66123
$n_{F'}$	480.0	1.66238
n_g	435.8	1.67249
n_h	404.7	1.68233
n_i	365.0	1.70029

Constants of Dispersion Formula	
A_0	2.6361862
A_1	$-9.0087536 \cdot 10^{-3}$
A_2	$2.5179779 \cdot 10^{-2}$
A_3	$1.1171914 \cdot 10^{-3}$
A_4	$-4.0112089 \cdot 10^{-5}$
A_5	$6.6254840 \cdot 10^{-6}$