

Refractive Indices		SF57
	λ [nm]	
$n_{2325.4}$	2325.4	1.79030
$n_{1970.1}$	1970.1	1.79540
$n_{1529.6}$	1529.6	1.80189
$n_{1060.0}$	1060.0	1.81184
n_t	1014.0	1.81337
n_s	852.1	1.82045
n_r	706.5	1.83104
n_C	656.3	1.83651
$n_{C'}$	643.8	1.83808
$n_{632.8}$	632.8	1.83957
n_D	589.3	1.84636
n_d	587.6	1.84666
n_e	546.1	1.85504
n_F	486.1	1.87205
$n_{F'}$	480.0	1.87425
n_g	435.8	1.89391
n_h	404.7	1.91363
n_i	365.0	1.95148

Constants of Dispersion Formula	
A_0	3.2578469
A_1	$-1.4544868 \cdot 10^{-2}$
A_2	$4.2028938 \cdot 10^{-2}$
A_3	$5.2295853 \cdot 10^{-3}$
A_4	$-4.6931979 \cdot 10^{-4}$
A_5	$4.4359036 \cdot 10^{-5}$