

Refractive Indices		SF58
	λ [nm]	
$n_{2325.4}$	2325.4	
$n_{1970.1}$	1970.1	
$n_{1529.6}$	1529.6	
$n_{1060.0}$	1060.0	1.87659
n_t	1014.0	1.87832
n_s	852.1	1.88648
n_r	706.5	1.89900
n_C	656.3	1.90550
$n_{C'}$	643.8	1.90738
$n_{632.8}$	632.8	1.90914
n_D	589.3	1.91725
n_d	587.6	1.91761
n_e	546.1	1.92765
n_F	486.1	1.94816
$n_{F'}$	480.0	1.95084
n_g	435.8	1.97486
n_h	404.7	1.99923
n_i	365.0	

Constants of Dispersion Formula	
A_0	3.4782654
A_1	$-1.0766912 \cdot 10^{-2}$
A_2	$5.8676907 \cdot 10^{-2}$
A_3	$4.2207315 \cdot 10^{-3}$
A_4	$-2.2895268 \cdot 10^{-4}$
A_5	$4.0847905 \cdot 10^{-5}$