

Refractive Indices		SF6
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.75306
$n_{1970.1}$	1970.1	1.75815
$n_{1529.6}$	1529.6	1.76447
$n_{1060.0}$	1060.0	1.77381
$n_t$	1014.0	1.77520
$n_s$	852.1	1.78159
$n_r$	706.5	1.79117
$n_C$	656.3	1.79609
$n_{C'}$	643.8	1.79750
$n_{632.8}$	632.8	1.79883
$n_D$	589.3	1.80491
$n_d$	587.6	1.80518
$n_e$	546.1	1.81265
$n_F$	486.1	1.82775
$n_{F'}$	480.0	1.82970
$n_g$	435.8	1.84705
$n_h$	404.7	1.86436
$n_i$	365.0	1.89716

Constants of Dispersion Formula	
$A_0$	3.1195007
$A_1$	$-1.0902580 \cdot 10^{-2}$
$A_2$	$4.1330651 \cdot 10^{-2}$
$A_3$	$3.1800214 \cdot 10^{-3}$
$A_4$	$-2.1953184 \cdot 10^{-4}$
$A_5$	$2.6671014 \cdot 10^{-5}$